

CAL TR 8X30

Granular Activated Carbon



Product Specification

Test	Specification		Calgon Carbon Test Method
	Min	Max	
DENSITY (APPARENT), g/cc	0.54	-	TM-7,ASTM D2854
ABRASION NUMBER	75	-	TM-9,AWWA B604
IODINE NUMBER, mg/g	950	-	TM-4,ASTM D4607
MOISTURE (AS PACKAGED), wt%	-	2	TM-1,ASTM D2867
MEAN PARTICLE DIAMETER, mm	1.1	1.4	TM-23,ASTM D2862
US SIEVE SERIES	-	-	

Typical Properties:

TCN (calculated)	14	TM-85
US SIEVE SERIES		ASTM D 2862
> 8 US MESH	1	
<35 US MESH	5	

Calgon Carbon Corporation's activated carbon products are continuously being improved and changes may have taken place since this publication went to press. (1806-10/16/2008)

Safety Message

Wet activated carbon preferentially removes oxygen from air. In closed or partially closed containers and vessels, oxygen depletion may reach hazardous levels. If workers are to enter a vessel containing carbon, appropriate sampling and work procedures for potentially low oxygen spaces should be followed, including all applicable Federal and State requirements.

27-267-11/90



Making Water and Air Safer and Cleaner

Your Local Representative

Calgon Carbon Corporation
P.O. Box 717
Pittsburgh, PA USA 15230-0717
1-800-422-7266
Tel: 1-412-787-6700
Fx: 1-412-787-6713

Chemviron Carbon
European Operations of
Calgon Carbon Corporation
Zoning Industriel C de Feluy
B-7181 Feluy, Belgium
Tel: + 32 (0) 64 51 18 11
Fx: + 32 (0) 64 54 15 91

Calgon Carbon Asia PTE LTD
9 Temasek Boulevard
#08-01A Suntec Tower Two
Singapore 038989
Tel: + 65 6 221 3500
Fx: + 65 6 221 3554