

Specification

Test	Min	Max	Calgon Carbon Test Method
IODINE NO., mg/g	900	-	ASTM D 4607
MOISTURE, wt%, as packed	-	5	ASTM D 2867
A.D., g/cc	0.44	0.49	ASTM D 2854
CARBON TETRACHLORIDE, wt%	55	-	ASTM D 3467-94, Note 2
US SIEVE SERIES			ASTM D 2862
> 4 US MESH	-	8	
6 US MESH	-	-	
8 US MESH	-	-	
10 US MESH	-	-	
< 10 US MESH	-	10	

Note 2: CCl₄ value may be based upon the ASTM D 5742 correlation, CCl₄ = 2.55 x Butane Activity.

Safety Message

Wet activated carbon preferentially removes oxygen from air. In closed or partially closed containers and vessels, oxygen depletion may reach hazardous levels. If workers are to enter a vessel containing carbon, appropriate sampling and work procedures for potentially low oxygen spaces should be followed, including all applicable Federal and State requirements.



CALGON CARBON CORPORATION

Calgon Carbon Corporation
P.O. Box 717
Pittsburgh, PA USA 15230-0717
1-800-422-7266
Tel: 1-412-787-6700
Fx: 1-412-787-6713

Making Water and Air Safer and Cleaner

Chemviron Carbon
European Operations of
Calgon Carbon Corporation
Zoning Industriel C de Feluy
B-7181 Feluy, Belgium
Tel: + 32 (0) 64 51 18 11
Fx: + 32 (0) 64 54 15 91

Calgon Carbon Asia PTE LTD
9 Temasek Boulevard
#08-01A Suntec Tower Two
Singapore 038989
Tel: + 65 6 221 3500
Fx: + 65 6 221 3554

Your local representative