

Specification

Test	Min	Max	Calgon Carbon Test Method
MOLASSES NO.	200	-	TM-3
IODINE NO., mg/g	950	-	TM-4 or ASTM D 4607
MOISTURE, wt%, as packed	-	3	TM-1 or ASTM D 2867
ABRASION NO.	70	-	TM-9
EXTRACTABLE pH	5.0	8.0	TM-15 or ASTM D 3838
ACID SOLUBLE ASH, wt%	-	0.5	TM-17
WATER SOLUBLE ASH, wt%	-	0.1	TM-16
US SIEVE SERIES			TM-8
+ 20	-	5	
- 50	-	1	

Safety Message

Wet activated carbon preferentially removes oxygen from air. In closed or partially closed containers and vessels, oxygen depletion may reach hazardous levels. If workers are to enter a vessel containing carbon, appropriate sampling and work procedures for potentially low oxygen spaces should be followed, including all applicable Federal and State requirements.



CALGON CARBON CORPORATION

Calgon Carbon Corporation
 P.O. Box 717
 Pittsburgh, PA USA 15230-0717
 1-800-422-7266
 Tel: 1-412-787-6700
 Fx: 1-412-787-6713

Making Water and Air Safer and Cleaner

Chemviron Carbon
 European Operations of
 Calgon Carbon Corporation
 Zoning Industriel C de Feluy
 B-7181 Feluy, Belgium
 Tel: + 32 (0) 64 51 18 11
 Fx: + 32 (0) 64 54 15 91

Calgon Carbon Asia PTE LTD
 9 Temasek Boulevard
 #08-01A Suntec Tower Two
 Singapore 038989
 Tel: + 65 6 221 3500
 Fx: + 65 6 221 3554

Your local representative